

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
28 December 2000 (28.12.2000)

PCT

(10) International Publication Number
WO 00/78858 A2

- (51) International Patent Classification⁷: **C08L 23/00**
- (21) International Application Number: **PCT/US00/17230**
- (22) International Filing Date: **23 June 2000 (23.06.2000)**
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data:
60/140,776 24 June 1999 (24.06.1999) US
60/197,050 14 April 2000 (14.04.2000) US
- (71) Applicant (for all designated States except US): **THE DOW CHEMICAL COMPANY** [US/US]; 2030 Dow Center, Midland, MI 48674 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **ANSEMS, Patricia** [NL/US]; 2118 Riverside Drive, West Columbia, TX 77486 (US). **SILVIS, H., Craig** [US/US]; 1908 Candlestick Lane, Midland, MI 48642 (US). **MADENJIAN, Lisa, S.** [US/US]; 110 Schrader Lane, Lake Jackson, TX 77566 (US).
- (74) Agent: **WAKEFIELD, Charles, P.**; Intellectual Property, B-1211, 2301 Brazosport Blvd., Freeport, TX 77541 (US).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:
— Without international search report and to be republished upon receipt of that report.
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 00/78858 A2

(54) Title: **POLYOLEFIN COMPOSITION WITH IMPROVED IMPACT PROPERTIES**

(57) Abstract: The present invention includes a composition comprising a coupled impact propylene copolymer. Preferably, the coupled impact propylene copolymer has an elastomeric phase that is present in an amount of at least 9 weight percent of the coupled propylene copolymer. Articles formed from the coupled propylene copolymer exhibit improved directionally balanced impact properties as compared with articles formed from comparable noncoupled impact propylene copolymers and also exhibit improved ductile-to-brittle transition temperatures compared with comparable noncoupled impact propylene copolymers. The invention also includes methods for making the coupled impact propylene copolymers using coupling agents, preferably, poly(sulfonyl azides). The invention further includes articles of manufacture that are made from the coupled impact propylene copolymer of the invention.

POLYOLEFIN COMPOSITION WITH IMPROVED IMPACT PROPERTIES

Background

To improve the impact properties of polypropylene
5 homopolymers (and random copolymers), an elastomeric
component is typically added, either by way of the
production of an in-reactor blend of a propylene polymer
and an elastomeric component (an impact propylene
copolymer) or by way of compounding of a propylene polymer
10 and an elastomeric component. In the former method the
propylene polymer and the elastomeric component are
produced in one or more reactors of the same process.

Both of these methods of improving the impact of
polypropylene do not significantly contribute to increasing
15 the melt strength of the resulting polypropylene impact
copolymer.

And although both methods result in a propylene
polymer with improved impact properties (when formed into
articles), these impact properties often show an imbalance
20 between the notched impact tested parallel to the polymer
injection flow direction of the injection molded product,
and the notched impact tested perpendicular to the polymer
injection flow direction of the injection molded product.
The notched impact tested on specimens cut perpendicular to
25 the direction of orientation (that is perpendicular to the
polymer injection flow direction), with the notch in the
direction of orientation (parallel to the polymer injection
flow direction), is typically much lower. The polymer
injection flow direction is the direction or line along
30 which the polymer is introduced into a mold or the
direction or line along which the polymer is extruded.

Polymers such as propylene polymers will tend to orient themselves along this line of direction.

What is desired is a polymer resin, which provides directionally balanced impact properties for articles made from the resin, while simultaneously having increased melt strength. Additionally, it would be desirable to provide a polymer resin, which is easy to fabricate into articles and exhibits a ductile-to-brittle transition temperature of 0°C or lower.

10

As used herein, the following terms shall have the following meanings:

"Coupling agent" means a chemical compound that contains at least two reactive groups that are each capable of forming a carbene or nitrene group that are capable of inserting into the carbon hydrogen bonds of CH, CH₂, or CH₃ groups, both aliphatic and aromatic, of a polymer chain. The reactive groups together can couple polymer chains. It may be necessary to activate a coupling agent with heat, sonic energy, radiation or other chemical activating energy, for the coupling agent to be effective for coupling polymer chains. Examples of chemical compounds that contain a reactive group capable of forming a carbene group include, for example, diazo alkanes, geminally-substituted methylene groups, and metallocarbenes. Examples of chemical compounds that contain reactive groups capable of forming nitrene groups, include, but are not limited to, for example, phosphazene azides, sulfonyl azides, formyl azides, and azides.

30

"Impact propylene copolymers" are commercially available and are well known within the skill in the art, for instance, as described by E.P. Moore, Jr in Polypropylene Handbook, Hanser Publishers, 1996, page 220-
5 221 and U.S. Patents 3,893,989 and 4,113,802. The term "impact propylene copolymer" is used herein to refer to heterophasic propylene copolymers where polypropylene is the continuous phase and an elastomeric phase is dispersed therein. Those of skill in the art recognize that this
10 elastomeric phase may also contain crystalline regions, which for purposes of the current invention are considered part of the elastomeric phase. The impact propylene copolymers result from an in-reactor process rather than physical blending. Usually the impact propylene
15 copolymers are formed in a dual or multi-stage process, which optionally involves a single reactor with at least two process stages taking place therein, or optionally multiple reactors.

"Impact properties" refer to properties of articles
20 such as impact strength, which is measured by any means within the skill in the art, for instance, Izod impact energy as measured in accordance with ASTM D 256, MTS Peak Impact Energy (dart impact) as measured in accordance with ASTM D 3763-93, and MTS total Impact Energy as measured in
25 accordance with ASTM D-3763. The ductile-to-brittle transition temperature (DBTT) is also an impact property of an article made from a polymer. The ductile-to-brittle transition temperature defines, for a given set of conditions, the temperature at which an object transitions
30 from a predominantly ductile mode of failure to a

predominantly brittle mode of failure. The ductile-to-brittle transition temperature can be calculated using techniques known to one of skill in the art.

5

Summary of the Invention

The invention includes a composition comprising a coupled impact propylene copolymer. The coupled impact propylene copolymer is formed by the reaction of a coupling
10 agent, such as a bis(sulfonyl azide), with an impact propylene copolymer. Advantageously, the impact propylene copolymers used for the invention have at least 5 weight percent, preferably at least 9 weight percent, more preferably at least 13 weight percent, of an elastomeric
15 phase based on the total weight of the impact propylene copolymer. Preferably, the elastomeric phase is less than 45 weight percent, more preferably less than 40 weight percent, most preferably less than 35 weight percent, of the total weight of the impact propylene copolymer.

20 When the continuous phase of the impact propylene copolymer is a homopolymer propylene polymer and the elastomeric phase is comprised of a copolymer or terpolymer containing monomer units derived from ethylene, the impact propylene copolymer preferably contains at least 5 weight
25 percent, more preferably at least 7 weight percent, most preferably at least 9 weight percent -CH₂CH₂- units derived from ethylene monomer based on the total weight of the impact propylene copolymer. Preferably, such an impact propylene copolymer contains less than 30 weight percent,
30 more preferably less than 25 weight percent, most

preferably less than 20 weight percent $-\text{CH}_2\text{CH}_2-$ units derived from ethylene monomer based on the total weight of the impact propylene copolymer.

The invention also includes a method for coupling an
5 impact propylene copolymer using a coupling agent, such as a bis(sulfonyl azide). The method improves the impact properties of the impact propylene copolymer and also increases the melt strength of the resulting coupled impact propylene copolymer resin to a level of at least 1.25
10 times, preferably at least 1.5 times, that of a comparable noncoupled impact propylene copolymer. All values for "melt strength" are determined by the method as set forth in the Examples. A comparable noncoupled impact propylene copolymer is the same polymer used to make the coupled
15 impact propylene copolymer, but has not been coupled. Preferably, the coupled impact propylene copolymer resins have a melt strength of at least 8 cN, more preferably a melt strength of at least 15cN, further more preferably a melt strength of at least 30 cN, most preferably a melt
20 strength of at least 50 cN and in some instances a melt strength of at least 60 cN.

Examples of impact properties that are improved in the coupled impact propylene copolymer of the invention compared to the comparable noncoupled impact propylene
25 copolymers, include: higher impact strength at low temperatures as exhibited by articles formed from the coupled impact propylene copolymer and an improvement in the ductile-to-brittle transition temperature, which is reduced in articles formed from the coupled impact
30 propylene copolymer of the invention.

Additionally, in all aspects, articles formed from the coupled impact propylene copolymer of the invention exhibit an improvement in the directional balance of the impact properties as compared to articles formed from a comparable noncoupled impact propylene copolymer. (that is a reduction of the imbalance between the impact properties as measured parallel to the polymer injection flow direction versus perpendicular to the polymer injection flow direction. This reduction in directional imbalance of the impact properties is indicated by a reduction in the difference between ductile-to-brittle transition temperatures measured parallel and perpendicular to the polymer injection flow direction for an article fabricated from the coupled impact propylene copolymer of the invention as compared with the difference between ductile-to-brittle transition temperatures measured parallel and perpendicular to the polymer injection flow direction for an article fabricated from a comparable noncoupled impact propylene copolymer.

In some aspects of the invention, the reduction in the DBTT for articles formed from the coupled impact propylene copolymer of the current invention versus articles formed from comparable noncoupled impact propylene copolymers (as calculated from the notched Izod values measured in accordance with ASTM D-256 with the notch perpendicular to the polymer injection flow direction) will be at least 10°C, preferably at least 15°C, more preferably at least 20°C and in some instances at least 25°C.

In another aspect of the invention, articles formed from the coupled impact propylene copolymers of the current invention exhibit a DBTT as calculated from notched Izod

values measured in accordance with ASTM D-256 with the notch perpendicular to the polymer injection flow direction, of -5°C or less, preferably of -10°C or less, more preferably of -15°C or less, most preferably -20°C or less.

For all the embodiments of the invention, the articles to be tested to determine DBTT should be edge-gated injection molded plaques that have a single polymer injection flow direction. For all embodiments, the Izod values are measured in accordance with ASTM D-256 and the values for DBTT are calculated in accordance with techniques known to one of ordinary skill in the art.

In a most preferred embodiment, articles made from the coupled impact propylene copolymers exhibit improvements in the directional balance of the impact properties together with improvements in the DBTT and a reduction of the DBTT as compared with comparable noncoupled impact propylene copolymers.

Further, articles formed from the coupled impact propylene copolymer resins of the present invention advantageously maintain the stiffness of the comparable noncoupled impact propylene copolymer.

Detailed Description of the Invention

The process to produce this improved impact propylene copolymer involves coupling of the impact propylene copolymer using a coupling agent. The coupling reaction is implemented via reactive extrusion or any other method which is capable of mixing the coupling agent with the impact propylene copolymer and adding sufficient energy to

cause a coupling reaction between the coupling agent and the impact propylene copolymer. Preferably, the process is carried out in a single vessel such as a melt mixer or a polymer extruder, such as described in WO 99/10424

5 published March 4, 1999. The term extruder is intended to include its broadest meaning and includes such devices as a device which extrudes pellets as well as an extruder which produces the extrudate for forming into films, blow molded articles, profile and sheet extruded articles, foams and
10 other articles.

As discussed earlier, the impact propylene copolymers have a continuous phase, which is comprised of a propylene polymer, and an elastomeric phase. The propylene polymer of the continuous phase typically will be a homopolymer
15 propylene polymer or a random propylene copolymer, more typically a homopolymer propylene polymer. The propylene polymer may be made using Ziegler-Natta catalyst, constrained geometry catalyst, metallocene catalyst, or any other suitable catalyst system. When the propylene
20 polymer making up the continuous phase is a homopolymer propylene polymer, the crystallinity of the propylene polymer, as determined by differential scanning calorimetry, is preferably at least 50 percent, more preferably at least 55 percent, most preferably at least
25 62 percent. The methods for determining percent crystallinity using a differential scanning calorimetry are known to one of skill in the art.

The elastomeric phase may be made using constrained geometry catalyst, Ziegler-Natta catalyst, metallocene
30 catalyst, or any other suitable catalyst.

The preferred coupling agent is a poly(sulfonyl azide), more preferably a bis(sulfonyl azide). Examples of poly(sulfonyl azides) useful for the invention are described in WO 99/10424. Poly(sulfonyl)azides include
5 such compounds as 1, 5-pentane bis(sulfonyl azide), 1,8-octane bis(sulfonyl azide), 1,10-decane bis(sulfonyl azide), 1,10-octadecane bis(sulfonyl azide), 1-octyl-2,4,6-benzene tris(sulfonyl azide), 4,4'-diphenyl ether bis(sulfonyl azide), 1,6-bis(4'-sulfonazidophenyl)hexane,
10 2,7-naphthalene bis(sulfonyl azide), and mixed sulfonyl azides of chlorinated aliphatic hydrocarbons containing an average of from 1 to 8 chlorine atoms and from 2 to 5 sulfonyl azide groups per molecule, and mixtures thereof. Preferred poly(sulfonyl azide)s include oxy-bis(4-
15 sulfonylazidobenzene), 2,7-naphthalene bis(sulfonyl azido), 4,4'-bis(sulfonyl azido)biphenyl, 4,4'-diphenyl ether bis(sulfonyl azide) and bis(4-sulfonyl azidophenyl)methane, and mixtures thereof.

Sulfonyl azides are commercially available or are
20 conveniently prepared by the reaction of sodium azide with the corresponding sulfonyl chloride, although oxidation of sulfonyl hydrazines with various reagents (nitrous acid, dinitrogen tetroxide, nitrosonium tetrafluoroborate) has been used.

25 In the practice of the invention preferably sufficient coupling agent is used to cause articles made from the resulting coupled impact propylene copolymer to exhibit a reduction in the difference between ductile-to-brittle transition temperatures measured parallel and perpendicular
30 to the polymer injection flow direction as compared with

the difference between ductile-to-brittle transition temperatures measured parallel and perpendicular to the polymer injection flow direction for an article fabricated from a comparable noncoupled impact propylene copolymer.

5 When a bis(sulfonyl azide) is used for the coupling agent, preferably at least 100 ppm of azide is used for coupling the impact propylene copolymer, based on the total weight of the impact propylene copolymer, more preferably at least 150 ppm of azide, most preferably at least 200 ppm of azide
10 is used. In some instances, such as where a large reduction in the ductile-to-brittle transition temperature is desirable as compared with the base comparable noncoupled impact propylene copolymer, at least 300 ppm of bis(sulfonyl azide), preferably at least 450 ppm of
15 bis(sulfonyl azide) based on the total weight of the impact propylene copolymer is used for coupling the impact propylene copolymer. It is important in choosing the impact propylene copolymer to be coupled, that a polymer is chosen that has a high enough melt flow rate, so that after
20 coupling with the desired amount of coupling agent, the coupled impact propylene copolymer will have a sufficiently high melt flow rate to be readily processed.

In a preferred aspect of the invention the coupled impact propylene copolymer of the invention can be
25 characterized by the following formula:

$$X = [(A-C)/(B-D)] \leq 0.75 \text{ and } Y \geq 1.25 \text{ and } A \leq B-10, \text{ in} \\ \text{which}$$

A = the ductile-to-brittle transition temperature
calculated from notched Izod values (Measured in accordance
with ASTM D-256) measured with the notch perpendicular to
the polymer injection flow direction for an article made
5 from the coupled impact propylene copolymer resin.

B = the ductile-to-brittle transition temperature
calculated from notched Izod values (Measured in accordance
with ASTM D-256) measured with the notch perpendicular to
the polymer injection flow direction for an article made
10 from the comparable noncoupled impact propylene copolymer
resin.

C = the ductile-to-brittle transition temperature
calculated from notched Izod values (Measured in accordance
with ASTM D-256) measured with the notch parallel to the
15 polymer injection flow direction for an article made from
the coupled impact propylene copolymer resin.

D = the ductile-to-brittle transition temperature
calculated from notched Izod (Measured in accordance with
ASTM D-256) measured with the notch parallel to the polymer
20 injection flow direction for an article made from the
comparable noncoupled impact propylene copolymer resin.

Y = the ratio of the melt strength of the coupled impact
propylene copolymer resin to the melt strength of the
comparable noncoupled impact propylene copolymer resin.
25 Preferably, in this aspect, Y is at least 1.5; more
preferably, Y is at least 2; most preferably, Y is at
least 5; and in some instances, Y is at least 10.

Preferably, in this aspect, X is less than 0.5, more
preferably less than 0.33, most preferably less than 0.25.

For purposes of this invention: the value for A above may sometimes be referred to as the "parallel ductile-to-brittle transition temperature" for an article made from the coupled impact propylene copolymer; the value for B
5 above may sometimes be referred to as the "parallel ductile-to-brittle transition temperature" for an article made from the comparable noncoupled impact propylene copolymer; the value for C above may sometimes be referred to as the "perpendicular ductile-to-brittle transition
10 temperature" for an article made from the coupled impact propylene copolymer; and the value for D above may sometimes be referred to as the "perpendicular ductile-to-brittle transition temperature" for an article made from the comparable noncoupled impact propylene copolymer.

15

Examples

Polypropylene impact copolymer C105-02, available from The Dow Chemical Company, is a high impact propylene copolymer with a melt flow rate of 1.5 g/10min and an
20 ethylene content of 16 wt percent was used to generate the results for Comparative Example 1. C105-02 was coupled with 450 ppm (based on the total weight of the polymers present) of 4,4'-oxy-bis-(sulfonylazido) benzene ("DPO-BSA") to produce the material used to generate the results
25 shown for Example 1. C105-02 was coupled with 200 ppm of 4,4'-oxy-bis-(sulfonylazido)benzene (based on the total weight of the polymers present) to produce the material used to generate the results shown for Example 3.

Polypropylene impact copolymer DC111, available from
30 the Dow Chemical Company, is a medium impact propylene

copolymer with a melt flow rate of 0.8 g/10min and an ethylene content of 9 wt percent was used to generate the results for Comparative Example 2. DC111 was coupled with 200 ppm of 4,4'-oxy-bis-(sulfonylazido)benzene (based on
5 the total weight of the polymers present) to produce the material used to generate the results shown for Example 2.

The preparation of the materials before extrusion was as follows:

10 For Example 1: the base resin C105-02 was tumbled with 2000 ppm of mineral oil for 30 minutes in drums, followed by the addition of 1000 ppm of tetrakis [Methylene (3,5-di-t-butyl-4-hydroxyhydrocinnamate)], which is available from the Ciba Specialty Chemicals Corporation under the
15 trade name Irganox¹ 1010, 1000 ppm of Irgafos² 168 and the desired amount of 4,4'-oxy-bis-(sulfonylazido)benzene. This mixture was then tumbled for another 30 minutes. This mixture was then extruded through an 11-barrel Werner&Pfleiderer ZSK40 twin screw extruder at a feed rate
20 of 250 lbs/hr, a screw speed of 300 rpm and with a target temperature profile of 180/190/200/200/210/220/230/240/230/240/240°C (from feed inlet to die).

25 For Example 2: A concentrate of 5 wt percent DPO-BSA in AFFINITY EG8200 (an ethylene-octene copolymer with a melt index of 5.0 g/min at 190°C, density 0.87 cm³ available from The Dow Chemical Company). This concentrate was fed simultaneously with the DC111 into the feed hopper of the

¹ Trademark of Ciba Specialty Chemicals Corporation

extruder described in Example 1. Sufficient concentrate was fed to add 200 ppm of DPO-BSA (based on total weight of the polymers present) to the material being extruded. The mixture was extruded as described for Example 1,
5 above.

For Example 3: A masterbatch of DPO-BSA in Profax 6501 (a 4 MFR propylene homopolymer available from Montell USA
10 INC.) with 1000 ppm of Irganox 1010 and 1000 ppm of Irgafos 168 was prepared by tumbling the components together. This masterbatch was fed simultaneously with the C105-02 into the feed hopper of the extruder described in Example 1. The masterbatch formed 5 wt percent of the
15 total material fed into the extruder and the amount of DPO-BSA added was sufficient to add 200 ppm of DPO-BSA (based on total weight of the polymers present) to the material being extruded. The mixture was extruded as described for Example 1, above

20

The resins for Comparative Example 1 and Comparative Example 2 and the resins obtained from Examples 1, 2 and 3 were tested for notched Izod at the temperatures as set forth in TABLES 1 and 2 following ASTM Method D-256 (as
25 described in The annual book of ASTM standards, Section 8: Plastics, 1997). Edge-gated plaques were injection molded, of which the required test samples were cut parallel and perpendicular to the polymer injection flow direction. After notching, samples were tested with the orientation

² Trademark of Ciba Specialty Chemicals Corporation

of the notch respectively perpendicular and parallel to the polymer injection flow direction.

The results of the impact testing are shown in the
5 tables below, in which bold numbers indicate a ductile
break. The data was analyzed using techniques known to one
of skill in the art to determine the DBTT for the polymer
resins of Comparative Examples 1 and 2 and Examples 1-3.
These values for DBTT along with other information are
10 listed in TABLE 3. The interpreted data show clearly that
the impact properties of articles made from the coupled
impact propylene copolymer resins of the Examples 1, 2,
and 3 are more directionally balanced than that the impact
properties of the articles made from the respective
15 comparable noncoupled impact propylene copolymer resins of
the Comparative Examples.

TABLE 1

Notched Izod With Notch Perpendicular to flow (J/m)					
Temperature (°C)	Example 1	Example 2	Example 3	Comparative Example 1	Comparative Example 2
20				801	
15				694	
10				534	368
5				160	342
0	587	641	747	160	171
-5		502	187	160	85
-10	641	379	171	107	91
-15	214			53	
-20	214	240	112	53	96
-25		75			

TABLE 2

Notched Izod With Notch Parallel to flow (J/m)					
Temperature (°C)	Example 1	Example 2	Example 3	Comparative Example 1	Comparative Example 2
23					235
20				587	
15				214	176
10			336	214	160
5			208	107	117
0	587	550	149	107	85
-5		240			
-10	480	117	112		75
-15	160				
-20	107	96	101		75

TABLE 3

	Example 1	Example 2	Example 3	Comparative Example 1	Comparative Example 2
A (°C)	-15.0	-20.0	-2.5		
B (°C)	7.5	2.5	7.5	7.5	2.5
C (°C)	-12.5	-7.5	5		
D (°C)	17.5	23.0	17.5	17.5	23.0
X	0.25	0.61	0.75	1.00	1.00
Melt Strength (cN)	64	70	8	5	7.9
Y	12.8	8.9	1.6		
A-B (°C)	-22.5	-22.5	-10.0		

Melt flow rate (MFR) for all the samples was measured at 230°C with a 2.16 kg weight according to the method of
 5 ASTM D1238.

Melt Strength for all the samples was measured by using a capillary rheometer fitted with a 2.1 mm diameter, 20:1 die with an entrance angle of approximately 45 degrees.
 10 After equilibrating the samples at 190°C for 10 minutes, the piston was run at a speed of 1 inch/minute. The standard test temperature is 190°C. The sample is drawn uniaxially to a set of accelerating nips located 100 mm below the die with an acceleration of 2.4 mm/sec². The required tensile force is
 15 recorded as a function of the take-up speed of the nip rolls. The maximum tensile force attained during the test is defined as the melt strength. In the case of polymer melt

exhibiting draw resonance, the tensile force before the onset of draw resonance was taken as melt strength. For the polymer of Example 1, the melt strength was 64 cN and the melt strength of the polymer of Comparative Example 1 was 5 cN.

The coupled impact propylene copolymer of the invention may advantageously be blended with other propylene polymers, including homopolymer propylene polymers, random propylene copolymers and other impact propylene polymers or with other polyolefins to make thermoplastic olefins (TPO's) or thermoplastic elastomers (TPE's); optionally the other propylene polymers or polyolefins may be coupled with coupling agents.

15

This invention is also useful for filled polypropylene systems, i.e. with mineral fillers such as talc or calcium carbonate. Additionally, it is believed that in some instances nucleating agents preferably may be utilized with the practice of the invention. These nucleating agents increase the rate at which the resins crystallize and, in some instances, may help lower the DBTT of articles formed from the resulting polymer resins. However, in some instances, the presence of a nucleating agent in a coupled impact propylene copolymer, may reduce the balance of the impact properties of an article formed from the coupled impact propylene copolymer. Examples of nucleating agents which may be used are NA-11, which is available from ASAHI DENKA Corporation.

25
30

The coupled impact propylene copolymers of the invention are useful for the fabrication of articles via (extrusion or injection) blow molding, injection molding, rotomolding, profile extrusion, sheet extrusion, pipe
5 extrusion, thermoforming, and foaming. These articles of manufacture will exhibit improved impact properties, including, improved directionally balanced impact properties, as compared with articles made from comparable noncoupled impact propylene copolymers.

10 The coupled impact propylene copolymers of the invention may also be formed into cast and blown film and may be used for extrusion coating. These coupled impact propylene copolymers are more readily processed into films under a wider range of processing conditions than
15 comparable noncoupled propylene copolymers.

We Claim:

1. A composition comprising a coupled impact propylene copolymer.
2. The composition of Claim 1, wherein the coupled
5 impact propylene copolymer is comprised of an elastomeric phase and wherein the elastomeric phase is present in an amount of at least 9 weight percent of the coupled impact propylene copolymer.
3. The composition of Claim 1, wherein the coupled
10 impact propylene copolymer is comprised of an elastomeric phase and wherein the elastomeric phase is present in an amount of at least 13 weight percent of the coupled impact propylene copolymer.
4. The composition of Claim 1, wherein the coupled
15 impact propylene copolymer is formed by the reaction of a coupling agent with an impact propylene copolymer.
5. The composition of Claim 4, wherein the coupling agent comprises a poly(sulfonyl azide).
6. The composition of Claim 5, wherein the coupling
20 agent comprises a bis(sulfonyl azide).
7. The composition of any of Claims 1-6, wherein an article formed from the coupled impact propylene copolymer exhibits improved directionally balanced impact properties as compared with an article formed from a comparable
25 noncoupled impact propylene copolymer.
8. The composition of Claim 7, wherein a parallel ductile-to-brittle transition temperature for the article formed from the coupled impact propylene copolymer is 10°C less than a parallel ductile-to-brittle transition

temperature for the article formed from the comparable noncoupled impact propylene copolymer.

9. The composition of Claim 7, wherein a parallel ductile-to-brittle transition temperature for the article
5 formed from the coupled impact propylene copolymer is 15°C less than a parallel ductile-to-brittle transition temperature for the article formed from the comparable noncoupled impact propylene copolymer.

10. The composition of Claim 7, wherein a parallel
10 ductile-to-brittle transition temperature for the article formed from the coupled impact propylene copolymer is 20°C less than a parallel ductile-to-brittle transition temperature for the article formed from the comparable noncoupled impact propylene copolymer.

15 11. The composition of Claim 7, wherein a parallel ductile-to-brittle transition temperature for the article formed from the coupled impact propylene copolymer is 25°C less than a parallel ductile-to-brittle transition temperature for the article formed from the comparable
20 noncoupled impact propylene copolymer.

12. The composition of Claim 7, wherein a parallel ductile-to-brittle transition temperature for the article formed from the coupled impact propylene copolymer is less than -5°C.

25 13. The composition of Claim 7, wherein a parallel ductile-to-brittle transition temperature for the article formed from the coupled impact propylene copolymer is less than -10°C.

14. The composition of Claim 7, wherein a parallel
30 ductile-to-brittle transition temperature for the article

formed from the coupled impact propylene copolymer is less than -15°C .

15. The composition of Claim 7, wherein a parallel ductile-to-brittle transition temperature for the article
5 formed from the coupled impact propylene copolymer is less than -20°C .

16. The composition of Claim 6, wherein a parallel ductile-to-brittle transition temperature for an article
10 formed from the coupled impact propylene copolymer is less than -10°C .

17. The composition of Claim 6, wherein a parallel ductile-to-brittle transition temperature for an article
15 formed from the coupled impact propylene copolymer is at least 10°C less than a parallel ductile-to-brittle transition temperature for an article formed from a comparable noncoupled impact propylene copolymers.

18. The composition of Claim 17, wherein the parallel ductile-to-brittle transition temperature for the
20 article formed from the coupled impact propylene copolymer is less than -15°C .

19. The composition of Claim 9, wherein the parallel ductile-to-brittle transition temperature for the article
formed from the coupled impact propylene copolymer is less than -15°C .

25 20. The composition of Claim 10, wherein the parallel ductile-to-brittle transition temperature for the article formed from the coupled impact propylene copolymer is less than -20°C .

21. The composition of Claim 1, wherein the coupled impact propylene copolymer is characterized by the following formula:

$$X = [(A-C)/(B-D)] \leq 0.75 \text{ and } Y \geq 1.25 \text{ and } A \leq B-10,$$

5

wherein:

A = a parallel ductile-to-brittle transition temperature for an article made from the coupled impact propylene copolymer;

10 B = a parallel ductile-to-brittle transition temperature for an article made from a comparable noncoupled impact propylene copolymer;

C = a perpendicular ductile-to-brittle transition temperature for the article made from the coupled impact
15 propylene copolymer;

D = a perpendicular ductile-to-brittle transition temperature for the article made from the comparable noncoupled impact propylene copolymer resin; and

Y = a ratio of a melt strength of the coupled impact
20 propylene copolymer to the melt strength of the comparable noncoupled impact propylene copolymer.

22. The composition of Claim 21, wherein Y is at least 1.5.

23. The composition of Claim 21, wherein Y is at
25 least 3.

24. The composition of Claim 21, wherein Y is at least 5.

25. The composition of Claim 21, wherein X is less than 0.5.

26. The composition of Claim 21, wherein X is less than 0.33.

27. The composition of Claim 21, wherein X is less than 0.25.

5 28. An article of manufacture comprising the composition of any of Claims 21-27, wherein the article of manufacture is selected from an extruded article, an injection molded article, a blow molded article, a bottle, a blow molded bottle, a rotomolded article, a profile
10 extruded article, an extruded sheet, a pipe extrusion, a thermoformed article, a foam or a combination thereof.

29. An article of manufacture comprising the composition of any of Claims 21-27, wherein the article of manufacture is a film.

15 30. A process for making a coupled impact propylene copolymer comprising the steps of: mixing a coupling agent with an impact propylene copolymer; and heating the mixture.

31. The process of Claim 30, wherein the process is
20 carried out in a mixer which mixes the coupling agent and the impact propylene copolymer and provides sufficient heat to cause reaction between the coupling agent and the impact propylene copolymer.

32. The process of Claim 30, wherein the process is
25 carried out in a polymer extruder.

33. The process of Claim 30, wherein the coupling agent comprises a poly(sulfonyl azide).

34. The process of Claim 30, wherein the coupling agent comprises a bis(sulfonyl azide).

35. The process of Claim 30, wherein the coupling agent comprises DPO-BSA.

36. The process of Claim 35, wherein at least 100ppm of the DPO-BSA is used based on the total weight of the
5 polymer present.

37. The process of Claim 35, wherein at least 200ppm of the DPO-BSA is used.

38. The process of Claim 35, wherein at least 450ppm of the DPO-BSA is used.